

## COMPARATIVE HARDNESS TABLE

Brinell hardness	Rockwell hardness	Rockwell hardness	Viskers-hardness
HB	HRB	HRC	HV
96	53		96
103	58,2		103
111	64,0		111
116	67,0		116
121	70,0		121
126	72,4		126
130	74,8		131
137	77,2		137
143	79,5		143
149	81,7		149
156	84,1		156
163	85,4		163
170	88,2		170
179	90,4		179
187	92,2		187
197	94,2		197
207	96,2		207
217	97,8		217
229	99,6	19,0	229
241	101,0	21,2	241
255	103,0	23,8	255
269	105,0	26,0	269

Brinell hardness	Rockwell hardness	Rockwell hardness	Viskers-hardness
HB	HRB	HRC	HV
285	107,0	28,3	285
302	109,0	30,5	302
321		32,8	321
341		35,0	341
363		37,4	364
388		40,2	393
415		43,2	430
444		47,0	466
478		49,0	510
541		52,0	560
555		56,0	640
600		59,0	695
611		59,3	704
622		60,5	726
632		61,5	750
643		62,5	774
654		63,5	800
665		64,5	826
676		65,5	855
688		67,0	903
694		68,0	940